



GLOBAL SAINI IMPORT EXPORT TRADING , CO..LTD

Address : No.240 Bui Thi Tu Nhien street , Dong Hai, HaiAn district , Haiphong city, VietNam

Email : sainiglobalexportimport@gmail.com

Tax code No : 0201900032

Whatsapp/Zalo /mobile : +84 81 696 4774

Website : <http://www.truchthon.com.vn>

Refractory Clay Bricks / QUANTITY : 7800 pcs /20'DC, 20pallets loaded

	STANDARD	FC-40 (A)	FC-35 (B)	FC-30 (C)
1	Al ₂ O ₃ , % Fe %	40 =< Al ₂ O ₃ < 45 3%	35 =< Al ₂ O ₃ < 40 3,5%	22 < Al ₂ O ₃ < 24 4,5 %
2	Refractoriness °C	≥1730	≥1650	≥1500
3	0.2MPa Refractoriness under load °C	≥1400	≥1350	≥1170
4	Permanent liner change%			
	1200 °C			0.6
	1300 °C		0.6	
	1400 °C	0.6		
5	Apparent Porosity %	≤22	≤23	≤24
6	Cold crushing strength Mpa	≥40	≥35	≥30
7	Bulk Density g/cm ³	≥2,0	≥1,95	≥1,90
8	Weight (kg /pcs)	3,5 kg	3,5 kg	3,5 kg
9	Size (mm)	230 x 114 x 65	230 x 114 x 65	230 x 114 x 65
10	ORIGINAL BRAND NAME	VIETNAM TRUCHTHON MANUFACTURE	VIETNAM TRUCHTHON MANUFACTURE	VIETNAM TRUCHTHON MANUFACTURE



